



WEST MICHIGAN RUBBER & SUPPLY
1.800.533.9677
sales@westmichiganrubber.com

RED SBR SHEET RUBBER

General Properties of SBR†

- Good physical properties.

† Properties shown based on Rubber Manufacturers Association Sheet Rubber Handbook, second edition.

SPECIFICATIONS:

Commercial grade red SBR sheet,
 Plate or Fabric Finish:

Style R75: 70 Duro hardness (Shore Durometer A)

Style RF75: 70 Duro hardness (Shore Durometer A)

Polymer: Styrene-Butadiene

Common Name: Red Rubber Sheet

ISO/ASTM Designation: SBR

Meets D1330 Grade 1

Style	ASTM Specification (SI units)	Temp. Range	Durometer	Tensile Strength (PSI)	Elongation (%)	Finish
R75	D 2000 M1AA 705	-22°F to +158°F	65 – 75	600	200%	Plate
RF75	D 2000 M1AA 705	-22°F to +158°F	65 – 75	600	200%	Fabric Impression

ORDERING INFORMATION:

Item Number		Gauge x Width (Inches)	Avg. Length (Linear Ft./Roll)	Approx. Wt./Roll
Plate Finish	Fabric Impression			
R75-02 x 36 x 67	RF75-02 x 36 x 67	1/16" x 36"	67 ft.	106 lbs.
R75-04 x 36 x 36	RF75-04 x 36 x 36	1/8" x 36"	36 ft.	114 lbs.
R75-06 x 36 x 36	RF75-06 x 36 x 36	3/16" x 36"	36 ft.	171 lbs.
R75-08 x 36 x 18	RF75-08 x 36 x 18	1/4" x 36"	18 ft.	114 lbs.
R75-02 x 48 x 67	RF75-02 x 48 x 67	1/16" x 48"	67 ft.	141 lbs.
R75-03 x 48 x 67	RF75-03 x 48 x 67	3/32" x 48"	67 ft.	211 lbs.
R75-04 x 48 x 36	RF75-04 x 48 x 36	1/8" x 48"	36 ft.	152 lbs.
R75-06 x 48 x 36	RF75-06 x 48 x 36	3/16" x 48"	36 ft.	228 lbs.
R75-08 x 48 x 18	RF75-08 x 48 x 18	1/4" x 48"	18 ft.	152 lbs.