



WEST MICHIGAN RUBBER & SUPPLY
1.800.533.9677
sales@westmichiganrubber.com

TAN PURE GUM SHEET RUBBER

General Properties of Pure Gum†

- Excellent physical properties
- Excellent abrasion-resistance
- Excellent low temperature resistance
- Good resistance to most acids

† Properties shown based on Rubber Manufacturers Association
Sheet Rubber Handbook, second edition.

SPECIFICATIONS:

Tan pure gum rubber sheet:

Style GF40: 40 Duro hardness (Shore Durometer A)

Polymer: Isoprene rubber (natural)

Common Name: Natural Rubber Sheet

ISO/ASTM Designation: NR

Style	ASTM Specification (SI units)	Temp. Range	Durometer	Tensile Strength (PSI)	Elongation (%)	Finish
GF40	D 2000 M1AA 424	-40°F to +176°F	35 – 45	3400	600%	Plate

ORDERING INFORMATION:

Item Number	Gauge x Width (Inches)	Avg. Length (Linear Ft./Roll)	Approx. Wt./Roll
GF40-02 x 36 x 67	1/16" x 36"	67 ft.	65 lbs.
GF40-04 x 36 x 67	1/8" x 36"	67 ft.	131 lbs.
GF40-06 x 36 x 67	3/16" x 36"	67 ft.	196 lbs.
GF40-08 x 36 x 36	1/4" x 36"	36 ft.	140 lbs.
GF40-12 x 36 x 36	3/8" x 36"	36 ft.	211 lbs.
GF40-16 x 36 x 18	1/2" x 36"	18 ft.	140 lbs.
GF40-24 x 36 x 18	3/4" x 36"	18 ft.	211 lbs.
GF40-32 x 36 x 18	1" x 36"	18 ft.	281 lbs.
GF40-02 x 48 x 67	1/16" x 48"	67 ft.	87 lbs.
GF40-04 x 48 x 36	1/8" x 48"	36 ft.	94 lbs.
GF40-06 x 48 x 36	3/16" x 48"	36 ft.	140 lbs.
GF40-08 x 48 x 18	1/4" x 48"	18 ft.	94 lbs.